



Distributed in the Interest  
of Product Development

# VANDERBILT

## Technical Data

Paint Department

**DARVAN® C-N** Dispersing Agent  
Anionic dispersing agent for water-borne paints and coatings

**DARVAN C-N** is a highly efficient anionic dispersing agent for mineral pigments and extenders used in both interior and exterior water-borne paints and coatings. Flat and semi-gloss finishes benefit from the use of **DARVAN C-N**.

### Typical Properties

Chemical Classification	Ammonium salt of polymethacrylic acid
Physical State	Pale straw colored liquid
% Active Solids	25%
Specific Gravity (25°C)	1.11 g/cc, 9.2 lbs/gal
pH	9.5-11.5
Viscosity (Brookfield 60 rpm)	<250 cps
VOC	<1 g/l
Recommended use level*	Flat paints: 2 to 5 lbs/100 gal Semi-gloss paints: 8 to 12 lbs/100 gal

\*The optimal amount of **DARVAN C-N** should be determined by the pigment dispersant demand curve method. A copy of the method is available on request.

**DARVAN** Dispersing Agent is a registered trademark of R.T. Vanderbilt Company, Inc.

06/11

**R.T. Vanderbilt Company, Inc., 30 Winfield Street, P.O. Box 5150, Norwalk, CT 06856-5150**  
**Telephone: (203) 853-1400 - Fax: (203) 853-1452 - Web Site: [www.rtvanderbilt.com](http://www.rtvanderbilt.com)**

Before using, read, understand and comply with the information and precautions in the Material Safety Data Sheets, label and other product literature. The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. R.T. Vanderbilt Company, Inc. does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent, trademark or copyright or to violate any federal, state or local law or regulation.