



Distributed in the Interest
of Product Development

VANDERBILT

Technical Data


Particles Size Analysis

R.T. Vanderbilt Company, Inc.
30 Winfield Street, P.O. Box 5150, Norwalk, CT 06856-5150
Telephone: (203) 853-1400
Fax: (203) 853-1452, Web Site: www.rtvanderbilt.com

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. R. T. Vanderbilt Company does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.



Differential Volume



Volume Statistics (Arithmetic)

Calculations from 0.429 µm to 900 µm

Volume	100.0%	95% Conf. Limits:	0-8.158 µm
Mean:	2.746 µm	S.D.:	2.761 µm
Median:	1.501 µm	Variance:	7.624 µm ²
Mean/Median Ratio:	1.829	C.V.:	101%
Mode:	0.931 µm	Skewness:	1.748 Right skewed
		Kurtosis:	2.724 Leptokurtic

% >	10	25	50	75	90
Size µm	6.836	3.753	1.501	0.859	0.609

**For additional information regarding our
high quality minerals and chemicals,
please visit our website:**

www.rtvanderbilt.com

- Technical data sheets
- MSDS information
- Sample requests
- Specifications
- Product brochures
- Articles
- Presentations
- Reports