



# R. T. Vanderbilt Company, Inc.

INDUSTRIAL MINERALS AND CHEMICALS

30 WINFIELD STREET, P.O. BOX 5150. NORWALK, CONNECTICUT 06856-5150 • (203) 853-1400  
Fax (203) 853-1452 • Internet Address: www.rtvanderbilt.com

# Specification

## VEEGUM® Granules

August 3, 2005

RTV Product Code: **71310**  
Composition: Magnesium aluminum silicate, purified smectite clay  
Physical State: Off-white granules

	<u>Specification</u>	<u>Test Method</u>
*Acid Demand	4.0 maximum	Current Volume USP/NF
*Al/Mg Ratio	0.5-1.2	Current Volume USP/NF
*Arsenic Content	3 ppm maximum	Current Volume USP/NF
*Lead Content	15 ppm maximum	Current Volume USP/NF
*Microbiology	**No more than 100 cfu/g bacteria **No more than 100 cfu/g fungi & yeast **No Escherichia coli **No Salmonella sp. **No Staphylococcus aureus **No Pseudomonas aeruginosa **No Gram negative organisms	Current Volume USP/NF Current Volume USP/NF Current Volume USP/NF Current Volume USP/NF Current Volume USP/NF Current Volume USP/NF T-968
*Moisture Content	8.0 maximum	Current Volume USP/NF
*pH, 5% Dispersion	9.0-10.0	Current Volume USP/NF
*Viscosity, Brookfield, 5% Dispersion	225-600 cps	Current Volume USP/NF
*X-ray Diffraction	Peaks between 1.492-1.504, 1.510- 1.540, and 15.0-17.2 Angstroms	Current Volume USP/NF

### GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Solubility - Insoluble, but dispersible in water

\*Certified Property

\*\*R.T. Vanderbilt Company certifies this result based on actual testing or the use of an irradiation process validated to achieve the indicated result.

VEEGUM is USP-NF Magnesium Aluminum Silicate, Type IA  
VEEGUM is INCI Magnesium Aluminum Silicate

*Uses - Please refer to VEEGUM Bulletin and Formulary*

*VEEGUM is a registered trademark of R.T. Vanderbilt Company, Inc.*

The information presented herein, while not guaranteed, was prepared by technical personnel and, to the best of our knowledge and belief, is true and accurate as of the date hereof. No warranty, representation or guarantee, express or implied, is made regarding accuracy, performance, stability, reliability or use. This information is not intended to be all-inclusive, because the manner and conditions of use, handling, storage and other factors may involve other or additional safety or performance considerations. The user is responsible for determining the suitability of any material for a specific purpose and for adopting such safety precautions as may be required. R.T. Vanderbilt Company does not warrant the results to be obtained in using any material, and disclaims all liability with respect to the use, handling or further processing of any such material. No suggestion for use is intended as, and nothing herein shall be construed as, a recommendation to infringe any existing patent or to violate any federal, state or local law or regulation.