



R. T. Vanderbilt Company, Inc.

INDUSTRIAL MINERALS AND CHEMICALS

30 WINFIELD STREET, P.O. BOX 5150. NORWALK, CONNECTICUT 06856-5150 • (203) 853-1400
Fax (203) 853-1452 • Internet Address: www.rtvanderbilt.com

Specification

LANGFORD CLAY

June 26, 2007

RTV Product Code: **09001**
Composition: Hydrated aluminum silicate, kaolin
Physical State: Cream powder

	<u>Specification</u>	<u>Test Method</u>
*Fineness, retained on 325 mesh	0.7% maximum	T-938
*Moisture Content	1.0% maximum	T-936

GENERAL INFORMATION

Typical values not routinely measured or reported on the Certificate of Analysis.

Brightness	70
Density at 25°C	2.62 Mg/m ³
Loss on Ignition	14.0%

*Certified Property

Uses - Low cost inert filler for all elastomers. Used in nonblack stocks of all types. Similar to McNAMEE CLAY, except for larger particle size, and lower color brightness.

Standard Container - 50 pound paper bag; bulk