

VISTALON™

Ethylene-Propylene Copolymer (EPM)
Effective September 13, 2005

Vistalon 706

SPECIFICATIONS

Property	Test Method ¹	Unit	Value
Mooney Viscosity ML 1 + 4 at 125°C	ASTM D 1646 ² , modified	-	42 ± 5
Ethylene Content	ASTM D 3900A	wt %	65 ± 2
Antioxidant Content Non-staining	ExxonMobil test method	wt %	0.10 ± 0.05
Vanadium	ExxonMobil test method	wppm	25 max.
Volatiles Content	ISO 248, modified	wt %	1.0 max.

¹ ExxonMobil test methods are available upon request.

² Radial cavity dies, polymer remassed at 145 ± 10°C.