

VISTALON™

Ethylene-Propylene Copolymer (EPM)
Effective May 27, 2005

Vistalon 878 Pellets

SPECIFICATIONS

Property	Test Method ¹	Unit	Value
Mooney Viscosity ML 1 + 4 at 125°C	ASTM D 1646 ² , modified	-	48 ± 7
Melt Index	ASTM D 1238 (cond F)	(190°C/21.6 kg)	6.5 target
Vanadium	ExxonMobil test method	wppm	25 max.
Volatiles	ASTM D 1278	wt %	0.3 max.
Color, Yellowness Index	ASTM E313-96		20 max.
Pellet Weight	Scale	g/30 pellets	0.6 ± 0.2

¹ ExxonMobil test methods are available upon request.

² Radial cavity dies, polymer remassed at 145 ± 10°C.

Pellets are dusted with HDPE powder.