

VISTALON™

Ethylene-Propylene Terpolymer (EPDM)
Effective September 13, 2005

Vistalon 1703P

SPECIFICATIONS

Property	Test Method ¹	Unit	Value
Mooney Viscosity ML 1 + 4 at 125°C	ASTM D 1646 ² , modified	-	25 ±5
Ethylene Content	ASTM D 3900B	wt %	76.8 ±1.5
VNB Content	ExxonMobil test method	wt %	0.9 ± 0.2
Vanadium	ExxonMobil test method	wppm	25 max
Volatiles	ASTM D 1278	wt %	0.3 max.
Color, Yellowness Index	ASTM E-313-96		20 max
Pellet Weight	Scale	grams/30 pell	1.1 ± 0.2

¹ ExxonMobil test methods are available upon request.

² Radial cavity dies, polymer remassed at 145 ± 10°C.

Pellets are dusted with LDPE powder.