

# VISTALON™

Ethylene-Propylene Terpolymer (EPDM)  
Effective September 13, 2005

## Vistalon 2727

### SPECIFICATIONS

Property	Test Method <sup>1</sup>	Unit	Value
Mooney Viscosity ML 1 + 4 at 125°C	ASTM D 1646 <sup>2</sup> , modified	-	44 ± 5
MLRA (1.6-5 s SR)	ASTM D 1646, modified	Mu*sec	195 ± 90
Ethylene Content	ASTM D 3900A	wt %	56.5 ± 2.0
ENB Content	ASTM D 6047	wt %	2.0 ± 0.25
Antioxidant Content Non-staining	ExxonMobil test method	wt %	0.01 - 0.08
Vanadium	ExxonMobil test method	wppm	25 max.
Volatiles Content	ISO 248, modified	wt %	0.6 max.

<sup>1</sup> ExxonMobil test methods are available upon request.

<sup>2</sup> Radial cavity dies, polymer remassed at 145 ± 10°C.