

VISTALON™

Ethylene-Propylene Terpolymer (EPDM)
Effective September 13, 2005

Vistalon 3702

Provisional Specifications for market development

Property	Test Method ¹	Unit	Value
Mooney Viscosity ML 1 + 4 at 125°C	ASTM D 1646 ² , modified	-	55 ±5
Ethylene Content	ASTM D 3900 A	wt %	69.0 ± 2.0
ENB Content	ASTM D 6047	wt %	2.8 ± 0.3
Antioxidant Content (non-staining)	ExxonMobil test method	wt %	0.15 ± 0.10

¹ ExxonMobil test methods are available upon request.

² Radial cavity dies, polymer remassed at 145 ± 10°C.