

VISTALON™

Ethylene-Propylene Terpolymer (EPDM)
Effective September 13, 2005

Vistalon 7001

Specifications

Property	Test Method ¹	Unit	Value
Mooney Viscosity ML 1 + 4 at 125°C	ASTM D 1646 ² , modified	-	60 ± 5
Ethylene Content	ASTM D 3900B	wt %	73.0 ± 2
ENB Content	ASTM D 6047	wt %	5.0 ± 0.4
Antioxidant Content non-staining	ExxonMobil test method	wt %	0.15 ± 0.10

¹ ExxonMobil test methods are available upon request

² Radial cavity dies, polymer remassed at 145 ± 10°C.