

# VISTALON™

Ethylene-Propylene Terpolymer (EPDM)  
Effective September 25, 2006

## Vistalon 7800P

### Provisional Specification

| Property                                   | Test Method <sup>1</sup> | Unit    | Value      |
|--|--------------------------|---------|------------|
| Melt Flow Rate (10kg/230°C) <sup>(2)</sup> | ASTM D 1238,<br>modified | g/10min | 12.5 ± 5.5 |
| Ethylene Content                           | ASTM D 3900              | wt %    | 79.0 ± 1.5 |
| ENB Content                                | ASTM D 6047              | wt %    | 6.0 ± 0.5  |
| Volatiles                                  | AM-S 350.03              | wt %    | 0.3 max.   |
| Colour (Yellowness Index Pellet)           | ASTM E 313,<br>modified  | -       | 18 max     |
| Pellets per gram                           | AM-S 98-012              | -       | 30 ± 10    |

<sup>1</sup> ExxonMobil test methods are available upon request.

<sup>2</sup> Correlated Mooney Viscosity 16 - 23 MU (ML 1+4 @ 125°C).